

EPR Insulation compound for Power Cables

Description

DYP-6603P is a cross-linkable insulation compound for power cables based on EPDM.(up to 35kV)

This compound provides good processing and long-run extrusion without scorch.

Specification

ICEA S-94-649

IEC 60502-2

BS 7655 1.2 type GP6

Typical Physical-Electrical Properties

Test items	Test method	Unit	Value
Specific Gravity at 23°C	ASTM D 792	-	1.20
Tensile Strength at break	IEC 60811-1-1	MPa	10
Elongation at break		%	400
M150		MPa	6
Hardness	ASTM D 2240	Shore A	85
Tb after ageing (Retention)	IEC 60811-1-2	%	>90
Eb after ageing (Retention) (After 168 hrs at 135°C)		%	>80
Hot set test (250°C, 15min, 20N/cm ²)	IEC 60811-2-1		
Elongation under load		%	25
Permanent elongation		%	5
Ozone resistance (0.025 ~ 0.03%, 24hrs)	IEC 60811-2-1	No crack	No crack
Water absorption (After 14 days at 85°C)	IEC 60811-1-3	mg/cm ²	0.6
Volume Resistivity at 23 °C	ASTM D 257	Ω·cm	5.0×10 ¹⁵
Dielectric strength	ASTM D 149		32
Dielectric constant, 60Hz	ASTM D 1531	kV/mm	2.50
		-	

* Data should not be used for specification work.

EPR Insulation compound for Power Cables

Processing Techniques

Recommending standard extrusion temperature profiles of **DYP-6603P** are as followings ; Unit: °C

Zone 1	Zone 2	Zone 3	Zone 4	Zone 5	Adapter	Head	Die
90±5	95±5	100±5	105±5	110±5	115±5	115±5	115±5

It is recommended that this product be processed using regular Metering(Single Flight) screw.
(L/D=20~24:1, C/R=1.8~2.5:1) Specific recommendations for Processing conditions can be determined only when the application and type of equipment are known.

Color & Appearance

This compound is an orange color and is supplied in pellet form.

Packing

Form : 550kg Cardboard Box (Inner PE bag packing)

Handling

To ensure health and safety, Material Safety Data Sheets(MSDS) is available on request.

Storage

Should be stored at room temperatures between 10~40°C. Recommended maximum storage period in a dry and clean place is 12months unopened and in original packaging after the manufacture.

Disclaimer

The product can be used only for the application as specified here above. It is the customer responsibility to inspect and test our products to satisfy the suitability of this product to customer's particular purpose. No liability can be accepted regarding the use of our products in conjunction with other materials. No warranties shall be offered which extend beyond the description contained here above. The above-mentioned information relates exclusively to our products when not used in conjunction with any third party materials.